



DRY LUBRICANTS SELECTION GUIDE



VICAFIL™

As the worldwide leader in wire drawing lubricants, CONDAT offers the industry's most extensive product range, covering the full spectrum of applications. Our wide range of formulations, including sodium-based, calcium-based and mixed-basis powder lubricants are designed to meet the latest environmental and health-&-safety regulations and directives, aimed to provide:

- Reduced dust levels in the workplace.
- Compliance with latest applicable legislations.
- Sustainable and environmentally-friendly solutions.

Our range has been developed to anticipate the market trends and meet or exceed our customer's expectations by offering the following potential advantages:

- Reduced soap consumption and waste disposal (and associated costs).
- Improved 'cleanability' (e.g. replacement of calcium soaps by sodium soaps).
- Optimized productivity by increased draw speeds.
- Improved adhesion (especially on smooth surfaces).

STEELSKIN™


A range of specialty lubricants, designed for the most demanding applications, formulated with a variety of additives, e.g.

- Extreme pressure (EP) additives (to reduce die wear).
- Graphite additives (to improve drawability).
- MoS₂ additives (to improve lubricity and reduce friction).
- Synthetic wax additives (to enhance lubricity and improve corrosion protection).

APPLICATIONS

Our range has been developed to cover a wide range of applications, including:

- Low, medium and high carbon steels (including zinc galvanized and aluminum clad).
- Stainless and nickel-based alloy steels.
- Non-ferrous materials, e.g. copper, aluminum and zinc.
- Cold rolling / roller-forming, e.g. welded mesh wire.
- Fastener industries (including nails, staples, rivets, and various CHQ fasteners).
- Spring wires (high carbon, stainless, oil-tempered etc.).
- Welding Wire (including CO₂, flux-cored and stick electrode).
- PC Strand and Rope.
- Drawing of bars (round and profiles).
- Fencing, industrial & agricultural wire.
- Tire cord and tire bead wire, etc



CONDAT

PROVIDING INNOVATION TO YOUR INDUSTRY

DRY LUBRICANTS SELECTION GUIDE



unless indicated

		STEEL						Stainless steel	Copper alloys	Aluminium alloys		
		Low carbon		High carbon		Alu clad	Galvanized					
		Mech. descaled	Acid-pickled and precoated	Mech. descaled	Acid-pickled and precoated							
VICAFIL™	Calcium soap based lubricants	CROCUS - X2 - TF 4407	•	•		•					Versatile for medium reductions and speeds.	
		TF 132 - TF 1562	•								Wire to be galvanized, low residues.	
		DECAL 600 -TF 44 - TF 812 DECAL 440	•						•			High lubricant pick-up.
		TF 239	•						•			High lubricant pick-up. Easy to remove
		X4			•	•		•				High speed drawing. Low consumption. Low dust.
		TF 1392 - X8*	•		•	•			•			High lubricant pick-up. Very high speed drawing.
		TF 1651	•		•	•						Redrawing : first drafts
		TF 1269	•		•	•						High speed drawing. Very good adherence. Low residues
		TF 120 - TF 3738 - DR				•			•			PC wire. Low dust and clean finish.
		CAULIS - CANTOR 60		•		•		•	•			Clean finish.
TF 1202 - TF 1669 - TF 1869				•		•	•			Galvanized wire. Spring wire. Very good adherence.		
LM 935 - LM 1120 - LAM 446	•									Cold rolling. Very low consumption.		
VICAFIL™	Sodium soap based lubricants	TN 4543	•	•							Clean finish. Few drafts. High reductions.	
		SPM 3 W - TN 3851*	•	•							Good drawing ability. Good cleaning ability.	
		TN 3952		•								Few reductions. 100% soluble in water : plating quality.
		TN 1700	•	•	•	•			•			Very high adherence. High lubricant pick-up.
		TN 1524		•		•			•			High speed drawing. First reductions. High cleaning ability.
		TN 1548* - TN 1678	•		•				•			First drafts instead of a calcium soap. Ex : CO2 Wire.
		TN 2693 - TN 1948*		•		•			•			Redrawing. Very good surface quality (Ex: spring wire).
		SALVIA 5 - TN 1180	•	•		•		•	•			General use redrawing. Very clean finish.
		SUMAC 3* - SANTALE 6 - SUMAC 5*	•	•	•	•		•	•			High performance requirements.
		TN 3774		•					•			CO ₂ Wire
TN 21 - TN 19T3		•		•		•	•			High speed drawing. Fine wire.		
SECALE - TN 3785		•		•		•		•		Bright and clean finish.		
TN 4392 - TN 1012 - SPS 99		•						•	•	Low speed drawing. Bright and clean finish.		
STEELSKIN™	Specialty lubricants	3814 - 2408		•		•		•			Cold heading wire. Low residues.	
		99 MO - 1091		•		•					Cold heading wire. Low residues. High tool life.	
		QBG 3					•		•		Aluminised steel (Alu clad)	
		121 - 4165				•					PC wire.	
		366						•			High drawing ability combined with a sodium soap.	
		DR				•			•		Redrawing. High pick-up.	
		5890 - 1670									Flux cored wire.	
		1629				•			•		Black finish.	
		4Z							•		Flux cored wire.	
		3150				•		•	•			Synthetic dry lubricant.
Powder GF			•	•			•			Additive. Synthetic graphite.		

* : <6,5% Borax

